

Document : SEMSD-07/06 First published: 24.01.2010 Revision Date : 25.03.2019

Page : 1/1

# **SMK-3349 SEMKYD FA 27 X 60**

## **DESCRIPTION**

SMK-3349 is a Special Fatty Acid Based Short Oil Alkyd Resin

# PRINCIPLE PROPERTIES

- ✓ Very fast drying
- ✓ High extender accepting
- ✓ High yellowing resistance
- ✓ Very good gloss and gloss retention

### RECOMENDED APPLICATIONS

- ✓ Very fast drying, high quality industrial primer and paints
- ✓ Hammertone Paints and Road Marking paints

## SOLUBILITY

Solvent Type	Solubility	
Toluene	+	
Xylene	+	
White Spirit	-	
n-Buthanol	-	
Methy-Ethyl Ketones	+	
Glycol Ethers	+	

## **COMPATIBILITY**

Resin Type	Compatibility	
Rosin Esters	-	
Amino Resins	+	
Short Oil Alkyds	+	
Medium Oil Alkyds	+	
Long Oil Alkyds	-	
Aliphatic Hardeners	+	
Aromatic Hardeners	+	
Cellulosic Resin	+	
Polyether Polyol	-	

## **TECHNICAL SPECIFICATIONS**

Composition		
Oil type	Special Fatty Acid	
Oil Lenght, %	~27%	
Solvent	Xylene	
PA Content, %	~34 %	
Appearence	Clear	
Test	Range	Method
Non Volatile, %	60±2 %	ISO 3251
Viscosity (25°C) Pa.s	4 – 10	ISO 3219
Acid Value (mgKOH/g)	10 max	ISO 2114
Color (Gardner)	7 max	ISO 4630-2
Density (g/cm³)	1,00±0,02	ISO 2811-1

### PACKAGING AND DELIVERY FORM

Resin is supplied in steel drum with net content of 200 Kg per drum. For the other package condition, please contact with us.

#### RECOMMENDED DRIER COMBINATIONS

Cobalt 0.04 - 0.06 % Zr 0.05 - 0.07 % 0.08 - 0.10 % Calcium

- As metals in relation to 100% resin

## **STORAGE AND SHELF LIFE**

Store in at temperatures between 5-30 °C, wellsealed packaging, dry and well-ventilated storage, should be avoided from direct sunlight.

Storage Shelf Life - 12 months from date of production.

#### **MATERIAL SAFETY**

Before handling the product, SDS of SMK-3349 should always be read and well understood. Safety prodecures should be followed.

This document is prepared by SEMKIM authorized person. To more information please visit www.semkim.com.tr

Kemalpaşa OSB Mh. 508 Sk. No:320, P:35730, Kemalpasa, İZMİR - TURKEY Tel: +90 232 878 97 80 (Pbx) Fax: +90 232 878 97 83

info@semkim.com.tr SEMFR-13